



**Cosmos Lac AE**

1 Pindou str.  
17672 Kallithea, Athens, Greece.  
Tel.: +30 2109570222 -  
Fax: +30 2109566671  
factory@cosmoslac.com  
www.cosmoslac.com

## Technical Data Sheet

<b>PRODUCT</b>	<b>COSMOS LAC EFFECT SPRAY 450 451</b>
<b>DESCRIPTION/USES</b>	High gloss decorative paint special for chrome or gold chrome effect in metallic and wooden surfaces. Chrome Effect has excellent coverage, excellent adhesion and a metallic gloss. Effect spray is not rub resistant and not resistant to weather influences.
<b>Color</b>	Chrome effect (450), Gold effect (451)
<b>Viscosity</b>	18-25 sec (Flow Cup DIN4, 20°C)
<b>Density</b>	0.6-0.8 g/L (Density Cup 100cm <sup>3</sup> /20°C, ASTM D – 1475)
<b>Solids w/w</b>	15-20%
<b>VOC content</b>	640 g/L
<b>Flash Point</b>	-104 °C (based on propellant)
<b>Drying time</b>	Touch (20°C, Humidity<65%): 5-10min Through dry (20°C, Humidity <65%) : 1h Maximum hardness: 24 hours
<b>Coverage</b>	5m <sup>2</sup> /L
<b>Gloss</b>	>90 GLOSS [ GLOSS METER 60 <sup>0</sup> ASTM D – 1471]
<b>Can Pressure</b>	4bar (20 °C) , 8 bar (50 °C)
<b>Contents</b>	400ml
<b>Application</b>	Remove all dust, rust and oil from the surface. Protect the area which you don't want to be painted. Shake the can thoroughly and spray at a distance of 30cm from the surface. Try the spray on testing surface. For better results apply 2-3 thin coats, 3-5 min apart. Best application temperature : 20 °C - 25 °C
<b>After use</b>	Spray holding the can inverted for 3". Clean the caps with solvent.
<b>Storage</b>	5-35°C. Do not put in vehicles.

ISSUED 27 November 2017, factory@cosmoslac.com