



**Cosmos Lac AE**

1 Pindou str.  
17672 Kallithea, Athens, Greece.  
Tel.: +30 2109570222 -  
Fax: +30 2109566671  
factory@cosmoslac.com  
www.cosmoslac.com

## Technical Data Sheet

<b>PRODUCT</b>	<b>COSMOS LAC Vinyl Spray 510</b>
<b>DESCRIPTION/USES</b>	Special spray based on vinyl resins suitable for repair and refresh of vinyl part of car and boat seats, luggage and any artificial leather part. Has maximum flexibility and maintains the original vinyl structure
<b>Available colors</b>	Black
<b>Viscosity</b>	18-25 sec (Flow Cup DIN4, 20°C)
<b>Density</b>	0.6-0.8 g/L (Density Cup 100cm <sup>3</sup> /20°C, ASTM D – 1475)
<b>Solids w/w</b>	15-20%
<b>VOC content</b>	500 g/L
<b>Flash Point</b>	-104 °C (based on propellant)
<b>Drying time</b>	Touch (20°C, Humidity<65%): 5-10min Through dry (20°C, Humidity <65%) : 1h Maximum hardness: 24 hours
<b>Coverage</b>	5m <sup>2</sup> /L
<b>Gloss</b>	Satin- Mat finish
<b>Can Pressure</b>	4bar (20 °C) , 8 bar (50 °C)
<b>Contents</b>	400ml
<b>Application</b>	Remove all dust, rust and oil from the surface. Protect the area which you don't want to be painted. Shake the can thoroughly and spray at a distance of 30cm from the surface. Try the spray on testing surface. Apply in several thin layers. For better results apply 2-3 thin coats, 3-5 min apart. Best application temperature : 20 °C - 25 °C
<b>After use</b>	Spray holding the can inverted for 3". Clean the caps with solvent.
<b>Storage</b>	5-35°C. Do not put in vehicles.

ISSUED 27 November 2017, factory@cosmoslac.com