



Technical datasheet

EXTREME TRAFFIC FLOOR VARNISH



Purpose:

Parquets, floors, stairs made of new or old wood. European or exotic wood.

Performances:

Ultra-high performance POLYCARBONATE floor varnish: forms a protective film combining both **HARDNESS**, for resistance against repeated use, scratches, water and stains, and **FLEXIBILITY** to absorb shocks without chipping.

Long lasting protection. High quality finishing: perfect flow. Gives warmth and depth to the wood. User-friendly: Ecolabel certified.

Preparation:

The wood must be bare, clean and dry.

- **BARE WOOD:** Mechanically sand the parquet with a sander (120 abrasive grit), then remove dust carefully.
- **VARNISHED WOOD:** mechanically sand the parquet twice (once with a 60 abrasive grit then 120) until bare wood is reached. Remove dust carefully.
- **WAXED AND OLD WOOD:** Remove wax then mechanically sand twice (once with 60 abrasive grit then 120) until bare wood is reached. Remove dust carefully.
- **Bare resinous wood (teak, doussie, etc.):** before applying your varnish, degrease wood.

Application:

Ideal conditions for application: between 12° and 25°C on a draught-free and dry floor. Milk-white appearance that disappears after drying.

1. Stir the floor varnish well before and during use with a long wide stick to homogenise.
2. Varnish using a supple-bristled brush or a 12-mm pile roller for special use with acrylic floor varnish.
3. Start with a corner of the room facing the daylight then move back till the exit.
4. Apply in regular full cross-coats then give the last stroke of your brush in the direction of the wood grain.
5. For optimum resistance, apply 3 coats of floor varnish or 2 coats after using the V33 Pre-Varnish Undercoat.
6. Between each coat, sand lightly (with a 240 abrasive grit) then remove dust to obtain a perfect flow.
7. Let dry for 24 hours.

V33 Suggests:

OLD PARQUETS: in order to avoid the formation of coloured stains (due to release of tannins), which can be frequent on old wood, before applying your floor varnish, apply V33 Pre-Varnish Undercoat (except before use of a medium oak coloured varnish).

Packaging: 0.75L-2.5L

Covering power in 1 coat for 2.5L: +/- 30m²

Drying: Between 2 coats: 2 hrs

Complete: 24 hrs

Cleaning of tools: Water

Equipment: Varnish roller or brush

SAFETY RECOMMENDATIONS and PRECAUTIONS FOR USE

S2: Keep out of the reach of children.

S29: Do not empty into drains.

S51: Use only in well-ventilated areas.

EU limit value for this product (cat. A/i): 140g/l (2010). This product contains max 40g/l VOC

NOVENTA S.A.

Πεθύμνου 1

106 82 Αθήνα

Tél : 210 – 8218502

Fax : 210 - 8218201

www.v33.com

G.S. Hadjiyiannis Logistics Ltd

PO Box 55004

3820 Limassol – Cyprus

+357-25-877430