DECOFIX	Technical Data Sheet (TDS) Declaration of Perfomance № 2257	COD: CC-PF-001 EDITIA: 1 REVIZIA: 0 DATA: 15.01.2020.

1 DATE : 09.08.2020.
2 Product Name: Fiberglass mesh 160 2000x2000
3 Production Date: 24.07.2020.
4 Storage Term: 2 years after date of production in dry Warehouse

№	Indicator	Meausure	Norm	Test result	Test Method
1	Number of threads 10 см (warp)	н/10 см y/10 cm	38-42	40	EAD 040016-00-0404:2016, Cl. 2.2.6
2	Number of threads 10 см (weft)	н/10 см y/10 cm	15-19	17	EAD 040016-00-0404:2016, Cl. 2.2.6
3	Width	см/cm	99,5-101	100	EAD 040016-00-0404:2016, Cl. 2.2.5
4	Mass per unit	г/м² gr/m²	144,2-165,9	160.9	EAD 040016-00-0404:2016, Cl. 2.2.8
5	Ash content	%	Not less than 15	18.18	EAD 040016-00-0404:2016, Cl. 2.2.2
6	Tearing Force (warp)	H/5 см N/5 cm	Not less than 2 000	2 509	u\o 040016-00-0404:2016, Cl. 2.2.7
7	Tearing Force (weft)	H/5 см N/5 cm	Not less than 2 000	2 626	u\o 040016-00-0404:2016, Cl. 2.2.7
8	Tearing Force after 28 days storage (warp)	H/50 мм N/50 mm	Not less than 1 000	1662	u\o 040016-00-0404:2016, Cl. 2.2.7
9	Tearing Force after 28 days storage (weft)	H/50 мм N/50 mm	Not less than 1 000	1 667	u\o 040016-00-0404:2016, Cl. 2.2.7
10	Cell size warp direction	мм/mm	Not less than 3	5.0	EAD 040016-00-0404:2016, Cl. 2.2.4
11	Cell size weft direction	мм/mm	Not less than 3	5.0	EAD 040016-00-0404:2016, Cl. 2.2.4